

23895 Nibionno (LC) Italy
via Volta, nr. 1 Bis
tel. +39 031 692.222 r.a.
imatex@imatex.it
www.imatex.it

TECHNICAL SHEET

Quality : CAPO	Design : 15/240/J
Composition	% 67%PC 14%PL 11%CO 8%MO
Finishing	J
Weight	gr/mtl 1020 ±5%
Useable width	cm 140
Horizontal repeat	cm
Vertical repeat	cm
Abrasion resistance EN ISO 12947-2 (Martindale method)	cycles 90.000
Abrasion resistance ASTM D4157 (Wyzenbeek method)	doublerubs
Pilling test EN ISO 12945-2 (Martindale method)	grade 4/ 5
Seam Slippage EN ISO 1936-2	warpways (mm) 4 weftways (mm) 3
Breaking Strength EN ISO 13934-1	warpways (N) weftways (N)
Tear Strength EN ISO 13937-3	AcrossWarp(N) AcrossWeft(N)
Colour Fastness to Light EN ISO 105 : B02	grade 5
Colour Fastness to Rubbing EN ISO 105-X12	dry (grade) 4/ 5 wet (grade) 4
Colour Fastness to Water EN ISO 105 : E01	staining (grade) change col. (grade)
Technical Bulletin 117-2013	results PASS
Cigarette test (BS 5852 : 2006 – Source 0)	results PASS
Match test (BS 5852 : 2006 – Source 1)	
Dimensional stability to washing	
Horizontal	%
Vertical	%
Cleaning instructions	    