

23895 Nibionno (LC) Italy
via Volta, nr. 1 Bis
tel. +39 031 692.222 r.a.
imatex@imatex.it
www.imatex.it

TECHNICAL SHEET

Quality : TADAO 1	Design : 96/7041/J	
Composition	%	46% WO 20% LI 19% PL 15% CO
Finishing		J
Weight	gr/mtl	700 ±5%
Useable width	cm	140
Horizontal repeat	cm	/
Vertical repeat	cm	/
Abrasion resistance EN ISO 12947-2 (Martindale method)	cycles	40.000
Abrasion resistance ASTM D4157 (Wyzenbeek method)	doublerubs	
Pilling test EN ISO 12945-2 (Martindale method)	grade	4
Seam Slippage EN ISO 1936-2	warpways (mm) weftways (mm)	4 4
Breaking Strength EN ISO 13934-1	warpways (N) weftways (N)	
Tear Strength EN ISO 13937-3	AcrossWarp(N) AcrossWeft(N)	
Colour Fastness to Light EN ISO 105 : B02	grade	5
Colour Fastness to Rubbing EN ISO 105-X12	dry (grade) wet (grade)	4/ 5 4
Colour Fastness to Water EN ISO 105 : E01	staining (grade) change col. (grade)	
Technical Bulletin 117-2013	results	PASS
Cigarette test (BS 5852 : 2006 – Source 0)	results	PASS
Match test (BS 5852 : 2006 – Source 1)		PASS
Dimensional stability to washing		
Horizontal	%	
Vertical	%	
Cleaning instructions	    	